

Product Data Sheet

CH1212WE/CH1212AE

| | | | |
|------------------------|---|----------------------------------|-----------------|
| Product Code No | ECONOMY QUALITY EXTERIOR ACRYLIC FLAT LATEX PAINT CH1212WE, CH1212AE | | |
| Type | EXTERIOR, ALKALINE RESISTANT, ACRYLIC LATEX | | |
| Description | The Economy Quality Exterior Acrylic Flat Latex Paint is a vinyl acrylic exterior flat latex. This product is very fast drying and it provides a quick cosmetic fresh appearance of a new paint job. It is easy to apply with very little spattering or roller drips. The finish shows good uniformity and color consistency. Its flat finish minimizes flashing on uneven surfaces. A highly alkaline primer sealer like the # CH1310WG, Good Quality Acrylic Latex Primer/ Sealer is recommended over all plaster and concrete substrates. | | |
| Uses | Exterior masonry, Concrete, Stucco walls | | |
| Colors | CH1212WE White and pastel tints CH1212AE Deep and accent tints | | |
| Gloss | Flat less than 10 units at 60 degrees | | |
| Coverage | 400 - 500 sq. ft. (37 to 46 sq. m.) per 3.78 l. (Values obtained on primed, smooth and non-porous surfaces. Coverage figures do not include any loss due to surface imperfections, porosity, mixing and application) | | |
| Dry time | To touch 1 – 2 hours Hard..... 2 - 3 hours Recoat..... 4 - 5 hours | | |
| Thinning | Clean water | | |
| Clean-up | Warm soapy water | | |
| Application | Surface to be painted must clean, dry and free from waxes, dirt, oils or other contaminants. Mildew must be treated with a bleach solution and removed by scrubbing and followed by rinsing with ample amount of clean water. Cracks and holes should be patched with a suitable exterior filling compound, allowed to dry thoroughly, and sanded smooth. All loose, flaking or peeling paint should be removed. New surfaces should be first painted with the # CH1310WG Acrylic Latex Primer / Sealer and allowed to dry completely. Air and surface temperature must be above 7 deg. C. Avoid painting in direct sunlight for maximum adhesion. Moisture content of any surface to be painted must be below 15%. | | |
| Method | Brush | Polyester/Nylon | Use as supplied |
| | Roller | Med. to Heavy pile, (18 - 28 mm) | Use as supplied |
| | Spray | .018 - .024 tip | Dilute 5% Max. |

All data on properties and application of the materials mentioned in this publication are given, to the best of our knowledge, based on our developmental work and practical experience. Before using our products, the user shall determine the suitability of the product for his independent use. In case of doubt, our technical staff will gladly assist you with expert advice. The data in this publication is subject to modification if deemed necessary to keep pace with new technical developments.